

LAMCO HPL FORM (HGP-VGP)

Material consisting of layers of kraft paper impregnated with thermosetting resins and a surface layer of decorative paper impregnated with aminoplastic resins, all bonded together by means of high pressure (9 Mpa) and high temperature (125-130° C). It is ideal to produce rounded edges for doors, shelves, sides, working surfaces and any other furniture components, reducing the dangers posed by sharp edges.
This material is produced in conformity to EN 438-3.

PROPERTY	TEST METHOD (EN 438: 2016)	PROPERTY OR ATTRIBUTE	UNIT	VALUES HGP	VALUES VGP
Thickness ± tolerance	EN 438-2.5	thickness (t)	mm	0,5 ≤ t ≤ 1,0 ±0,10 1,0 < t < 2,0 ±0,15	0,5 ≤ t ≤ 1,0 ±0,10 1,0 < t ≤ 1,2 ±0,15
Flatness	EN 438-2.9	maximum deviation	mm/mtl	60	60
Resistance to surface wear	EN 438-2.10	wear resistance	revs	IP ≥ 150	IP ≥ 50
Resistance to immersion in boiling water	EN 438-2.12	appearance gloss finish appearance other finishes	rating	≥ 3 ≥ 4	≥ 3 ≥ 4
Resistance to dry heat (160°C)	EN 438-2.16	appearance gloss finish appearance other finishes	rating	≥ 3 ≥ 4	≥ 3 ≥ 4
Resistance to wet heat (100°C)	EN 438-2.18	appearance gloss finish appearance other finishes	rating	≥ 3 ≥ 4	≥ 3 ≥ 4
Dimensional stability at elevated temperature	EN 438-2.17	cumulative dimensional change	% long. % transv.	≤ 0,55 ≤ 1,05	≤ 0,75 ≤ 1,25
Resistance to impact by small diameter ball	EN 438-2.20	spring force	N	≥ 20	≥ 15
Resistance to cracking	EN 438-2.23	appearance	rating	≥ 4	≥ 4
Resistance to scratching⁽¹⁾	EN 438-2.25	appearance gloss finish appearance other finishes	rating	≥ 2 ≥ 3	≥ 1 ≥ 2
Resistance to staining	EN 438-2.26	app. groups 1-2 appear. groups 3	rating	5 ≥ 4	5 ≥ 4
Lightfastness	EN 438-2.27	contrast	grey scale rating	≥ 4	≥ 4
Resistance to water vapour	EN 438-2.14	appearance gloss finish appearance other finishes	rating	≥ 3 ≥ 4	≥ 3 ≥ 4
Formability	EN 438-2.32	radius	mm	≤ t x 10 long. ≤ t x 20 trasv.	≤ t x 10 long. ≤ t x 20 trasv.
Resistance to blistering	EN 438-2.34	time	sec.	t < 0,8 mm: ≥ 10 t ≥ 0,8 mm: ≥ 15	t < 0,8 mm: ≥ 10 t ≥ 0,8 mm: ≥ 15
Electrical resistance	EN 61340-4-1	R _v (23°C /50% RH)	Ohm	10 ⁹ - 10 ¹¹	10 ⁹ - 10 ¹¹
Density	ISO 1183	density	gr/cm ³	≥ 1,40	≥ 1,40

(1) Resistance to scratching is depending from finish and colour.

Note: The colour of individual lots may vary as a result of the technology and type of pigment used. Pay attention to the direction of the texture.

LAMCO HPL FORM (HGP-VGP)

FIRE PERFORMANCE

TEST METHOD	STANDARD	CLASSIFICATION	
		HGP/VGP flame retardant	HGP/VGP
Small flame and radiant panel	UNI 8457 UNI 9174 UNI 9177	class 1	class 1
Spread of flame	BS 476-7	class 1	class 2
Brandschacht	DIN4102-1	B1	B2
Epiradiateur	NF P 92-501	M1	min. M3
Smoke density and toxicity	NF F 16-101	min F2	min F2
Heat release	IMO Res. A 653(16)	pass	pass

Note: Fire test performance will depend on laminate thickness and construction, substrate type and thickness, and adhesive used.